



Product Name	Exothermic Welding Mould
Product Code	Refer to Catalogue page 12 to 20
Application	Grounding/Earthing And Lightning Protection Cathodic Protection
Applicable Standards	IEEE 837 std.



Product Information	
Material	Graphite
Durability	At least 50 No. of Weld
True Density	2.20-2.23 (g/cm <sup>3</sup> )
Thermal Expansion	0.4-0.8 (X10-6/°C)
Mechanical Strength	10~14 (MPa)
Manufacturing Method	Milling And CNC Milling
Max. Ash Content	0.2%
Due to low Thermal Expansion of material High Working Temperature will not result in Fatigue and Destruction of Moulds	

