



Product Name	Carbon Based BackFill
Product Code	MLO2
Application	Grounding/Earthing And Lightning Protection
Applicable Standards	IEC/BS EN 62561-7 IGS-I-EL-001(0)



Product Information	
Resistivity	0.42 Ωm
Polarization Resistance	8.11 $\Omega.\text{m}^2$
PAH	<0.0002 mg/L
Sulphur Content	<1%
Carbon Content	+75%
Pack Weight	15kg
Dry Density	1146 Kg/m^3
Mix Ratio	15kg MLO2 Mixed With 10kg Concrete + 14 L Water



Do not Mix MLO2 With Salt Water.

MLO2 & Concrete Will Sets within 5Hours , Fully Cures within 28 Days

MLO2 Mixture Does not Dissolve , Decompose or Leach out.

CAJHIZAT SYSTEM ZAMIN CO.

Tel: +98 21 77940716/77959032

Fax: +98 21 77953528

E-Mail: Info@tsamin.com

