



Product Name	Conductive Concrete
Product Code	MLO3
Application	Grounding/Earthing And Lightning Protection
Applicable Standards	IEC/BS EN 62561-7 IGS-I-EL-001(0)

Product Information	
Resistivity	0.42 Ωm
Polarization Resistance	8.11 $\Omega.\text{m}^2$
PAH	<0.0002 mg/L
Sulphur Content	<1%
Curing Duration	5Hours to solidify and 28 Days to fully cure
Pack Weight	15kg
Dry Density	2400 Kg/m ³
Mortar Mix Ratio.	15kg MLO3 + 14 L Water
Do not Mix MLO3 With Salt Water. MLO3 Mixture Does not Dissolve, Decompose or Leach out. Do not Mix Sand or Gravel with MLO3.	

**CAJHIZAT SYSTEM ZAMIN CO.**

Tel: +98 21 77940716/77959032

Fax: +98 21 77953528

E-Mail: Info@tsamin.com

